

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 0 369 658 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention
of the grant of the patent:
05.08.1998 Bulletin 1998/32

(51) Int Cl.⁶: C08J 5/18, C08L 23/10

(21) Application number: 89311427.2

(22) Date of filing: 03.11.1989

(54) **Polypropylène stretched film**

Gestreckter Polypropylen-Film

Film de polypropylène étiré

(84) Designated Contracting States:
DE FR GB IT

(30) Priority: 16.11.1988 JP 290920/88

(43) Date of publication of application:
23.05.1990 Bulletin 1990/21

(73) Proprietor: SUMITOMO CHEMICAL COMPANY
LIMITED
Osaka-shi, Osaka 541 (JP)

(72) Inventors:
• Ogawa, Tadatoshi
Singapore 0923 (SG)

- Ima, Seiichiro
Ichihara-shi (JP)
- Wakamatsu, Kazuki
Kimitsu-gun Chiba-ken (JP)

(74) Representative: Ablewhite, Alan James et al
MARKS & CLERK,
57/60 Lincoln's Inn Fields
London WC2A 3LS (GB)

(56) References cited:
EP-A- 0 151 883 EP-A- 0 152 701
EP-A- 0 227 300

EP 0 369 658 B1

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description

The present invention relates to a polypropylene stretched film. In more particular, it relates to a polypropylene stretched film having a high rigidity and a beautiful appearance including transparency.

Polypropylene stretched films are good in optical properties, mechanical properties, and suitability for packaging. Hence they have been widely used in the field of packaging including food packaging and textile product packaging. However, the conventional polypropylene stretched films are, for some uses, unsatisfactory in mechanical properties, particularly in rigidity. Therefore, the improvement of such properties has been eagerly desired. Accordingly, there have been proposed a number of proposals for improving the rigidity of polypropylene stretched film. For example, JP-B-47-11656 and 54-15779 propose a method which comprises adding modifiers of petroleum resins such as styrenic hydrocarbon polymers to polypropylenes.

EP-A-152-701 discloses a method of producing a propylene copolymer having improved rigidity and transparency, which comprises a mixture of polypropylene and vinyl cycloalkane. Also, EP-A-227-300 discloses an electrical insulating material which comprises adding a small amount of a 3-branched α -olefin and/or vinylcycloalkane to polypropylenes. JP-A-55-81125 proposes a method which comprises using a polypropylene of which the isotactic pentad fraction of boiling heptane insoluble portion is 0.955 or more.

Further, JP-A-56-2307, 59-172507 and 62-195007 teach a method for improving the rigidity of polypropylene itself which comprises widening the molecular weight distribution.

For improving the transparency and other appearances of polypropylene stretched films, JP-B-54-15779 discloses a method comprising adding petroleum resins to polypropylene. JP-B-60-43859 and JP-A-60-139428 disclose methods comprising adding a sorbitol derivative or a specific polymeric nucleating agent to polypropylene. EP-A-151-883 discloses a polymer composition comprising a mixture of crystalline polypropylene and vinyl cycloalkane, which has enhanced crystallinity and transparency.

However, these methods disclosed in the above-mentioned documents each have a problem of insufficient improvement in rigidity and transparency, or deterioration of characteristic properties inherent to crystalline propylene polymers, or severe fuming or roll staining during film forming operation.

Thus, in the methods comprising adding modifiers of petroleum resins to polypropylene, although the rigidity and transparency of the product are improved to some extent, the heat resistance and solvent resistance are deteriorated, posing restriction to the use thereof, and moreover severe fuming and roll staining take place during film forming operation. In the method which uses polypropylene having an isotactic pentad fraction of boiling-heptane insoluble portion of 0.955 or more, the rigidity is improved to some extent but it is not yet sufficient, and further the transparency is unsatisfactory. In the method which comprises widening the molecular weight distribution of polypropylene, the rigidity is improved to some extent but it is not sufficient, and moreover, the transparency is very unsatisfactory, also.

In the methods comprising mere addition of sorbitol derivatives or polymeric nucleating agents, no improvement in the rigidity of polypropylene stretched film is recognized although the transparency is improved to some extent.

According to the present invention, there is provided a polypropylene stretched film consisting essentially of a composition which comprises a crystalline propylene polymer and 0.1 ppm by weight to 10% by weight of a nucleating agent, the composition having a melting point of 160°C or more, a crystallization temperature of 128°C or more, and a 20°C xylene soluble portion of 3.0% by weight or less.

When the composition contains a nucleating agent in a content outside the range of from 0.1 ppm by weight to 10% by weight, a melting point of less than 160°C, a crystallization temperature of less than 128°C, or a 20°C xylene soluble portion of more than 3.0% by weight, the resulting film is unsatisfactory in rigidity or transparency and the merits of the present invention cannot be achieved.

The composition used in the present invention comprising a polypropylene stretched film consisting essentially of a composition which comprises a crystalline propylene polymer and a polymer of a vinylcycloalkane, the composition having a melting point of 160°C or more, a crystallization temperature of 128°C or more and a 20°C xylene soluble portion of 3.0% by weight or less characterised in that the film is transparent and the vinylcycloalkane polymer is a vinylcycloalkane polymer which is present in an amount from 10,500 ppm to 10% by weight.

The melt flow rate of the composition is not critical. However, it is preferably 10 g/10 min or less, more preferably 1.0 - 8.0 g/10 min, and most preferably 1.0 - 6.5 g/10 min.

Although the nucleating agent used in the present invention is not critical, it is preferably a polymer of an α -olefin having 6 or more carbon atoms branched at the 3-position or a copolymer of a vinylcycloalkane, and more preferably a polymer of vinylcyclohexane.

A content of the nucleating agent less than 0.1 ppm by weight is unpreferable since it gives the product an unsatisfactory rigidity and transparency. A content of the nucleating agent exceeding 10% by weight is unpreferable from the viewpoint of processability and cost factor. The content preferably falls in the range of from 2 ppm by weight to 5% by weight, more preferably from 2 ppm by weight to 3% by weight and most preferably from 100 ppm by weight to 3% by weight.

The process for preparing the composition comprising a crystalline propylene polymer and a nucleating agent used in the present invention is not critical so long as the process gives a composition which satisfies the limitations of the present invention. For example, the composition can be prepared by polymerizing a vinyl compound such as vinylcyclohexane with a known Ziegler-Natta catalyst containing a titanium compound, organoaluminum compound and electron donating compound at the first stage and then polymerizing propylene at the second stage. Alternatively, it can be prepared by polymerizing propylene at the first stage, polymerizing a vinyl compound at the second stage, and then polymerizing propylene again at the third stage.

To the composition used in the present invention may be added as occasion demands various additives usually used for polypropylene, such as antioxidants, lubricants, antistatic agents and antiblocking agents.

The polypropylene stretched film of the present invention may be prepared by stretching polypropylene film in at least one direction in a usual manner, for example roll stretching, tenter stretching and tubular stretching. The film is usually stretched 5-100 times that of the original area.

The polypropylene stretched film of the present invention may be subjected to a surface treatment such as corona discharge treatment or flame treatment in a conventional manner.

The polypropylene stretched film of the present invention has a high rigidity and a beautiful appearance, so that it may be used as it is. It may also be used as the base layer of a composite film provided with a heat-sealable layer etc. at least on one side. Such a composite film is particularly suited for packaging.

The present invention will be described further in detail below with reference to Examples, but the scope of the present invention is in no way limited by the Examples.

The characteristic properties of the polypropylene, composition or stretched film mentioned in the Specification and Claims of the present invention are determined by the following methods.

(1) Melt flow rate (MFR)

Determination was made according to JIS K 7210, Condition-14.

(2) Molecular weight distribution (M_w/M_n)

Determination was made with gel permeation chromatography (GPC) under the following conditions. The calibration curve was prepared with a standard polystyrene.

Apparatus : Type 150C, mfd. by Millipore Waters Corp.; column : Shodex M/S800; measuring temperature : 140°C; solvent : o-dichlorobenzene; sample concentration : 5 mg/8 ml

(3) Melting point (T_m) and crystallization temperature (T_c)

Determination was made with a differential scanning calorimeter (DSC, mfd. by Perkin-Elmer Inc.). A specimen weighing 10 mg was molten in nitrogen atmosphere at 220°C for 5 minutes, and then the temperature was lowered down to 40°C at a rate of 5°C/min to obtain a crystallization heat-evolution curve. The temperature of the maximum peak of the curve was taken as the crystallization temperature. Thereafter, the temperature was raised at a rate of 5°C/min to obtain a melting heat-adsorption curve. The temperature of the maximum peak of the curve was taken as the melting point.

(4) 20°C Xylene soluble portion (CXS)

One gram of polypropylene was dissolved completely in 100 ml of boiling xylene, and the solution was then brought to 20°C and allowed to stand for 4 hours. Thereafter, the formed precipitate was separated by filtration from the solution. The filtrate was evaporated to dryness and further dried under reduced pressure at 70°C. The dried product was weighed to determine the content of the xylene soluble portion (% by weight).

(5) Scattering-transmitted light intensity (LSI)

Determination was made with an LSI Tester (mfd. by Toyo Seiki, Inc.) by receiving scattering-transmitted light in the range of 1.2 - 3.6°. Since the LSI value corresponded quite well to the visually-observed, see-through clarity in the case of polypropylene stretched film, it was taken as the measure of transparency.

(6) Young's modulus

A test piece 20 mm in width was taken along the longitudinal direction (MD) and stretched with a tensile tester at

a distance between grips of 60 mm and a stretching velocity of 5 mm/min to obtain an S-S curve, from which the initial modulus of elasticity was determined.

Example 1

(1) Preparation of solid catalyst

(i) Synthesis of solid product

The inner atmosphere of a flask of 5-ℓ inner volume fitted with a stirrer and dropping funnel was replaced by argon. Then, 1,100 ml of n-heptane and 670 ml of tetra-n-butoxytitanium were put into the flask, and the temperature in the flask was kept at 35°C. A solution consisting of 1,080 ml of n-heptane and 445 ml of ethylaluminum sesquichloride was gradually introduced by drops into the flask from the dropping funnel over a period of 2 hours while the temperature in the flask was kept at 35°C. After completion of the dropwise introduction, the temperature was raised to 60°C and the reaction mixture was stirred for one hour. The mixture was allowed to stand at room temperature and separated into solid and liquid. The solid was washed 4 times repeatedly with 1,000 ml of n-heptane and dried under reduced pressure to obtain a reddish brown solid product. The solid product contained 5.2 mmol of titanium and 7.0 mmol of the n-butoxy group per gram of the solid product.

(ii) Synthesis of solid catalyst component

The inner atmosphere of a flask of 1-ℓ inner volume was replaced by argon. Then, 54 g of the solid product prepared in the above item (i) and 270 ml of n-heptane were put into the flask and the temperature in the flask was kept at 65°C. Then, 48 ml of di-n-butyl ether and 156 ml of titanium tetrachloride were added thereto. The resultant mixture was allowed to react at 65°C for one hour. Then, the reaction mixture was allowed to stand at room temperature and separated into solid and liquid. The solid thus obtained was washed 4 times repeatedly with 500 ml of n-heptane and dried under reduced pressure to obtain a solid catalyst component (hereinafter the solid catalyst component (a)). Subsequently, 600 ml of dehydrated and purified n-heptane, 16.5 mmol of diethylaluminum chloride and 50 g of the solid catalyst component (a) prepared above were put in succession into a 1-ℓ glass flask. The resulting mixture was adjusted to a temperature of 60°C. Then, propylene was fed into the flask to keep a pressure of 200 mmHg over atmospheric pressure and polymerization was thus carried out until the amount of fed propylene reached 40 g. Subsequently, 170 ml of vinylcyclohexane was fed over a period of one hour and polymerization was continued for further two hours. The solid catalyst containing polymers of propylene and vinylcyclohexane thus obtained was washed with 200 ml of dehydrated and purified n-heptane. Then, the solid catalyst was dried to obtain 222 g of a solid catalyst containing 40 g of propylene polymerization units and 132 g of vinylcyclohexane polymerization units (hereinafter the solid-catalyst (b)).

(2) Preparation of composition

Into a 0.33-m³ stainless steel (SUS) reactor fitted with a stirrer which had been adjusted with propylene to a gauge pressure of 0.5 kg/cm² and kept at 35°C were introduced 0.16 m³ of n-heptane, 1.2 mol of diethylaluminum chloride and 0.1 mol of methyl methacrylate in succession, and then 150 g of the solid catalyst (b) prepared above, 20 kg of propylene and 75 ℓ of hydrogen. The temperature was then raised to 60°C and polymerization was initiated. The polymerization was continued by feeding propylene to keep a polymerization pressure of 6 kg/cm² gauge and feeding hydrogen to keep a hydrogen concentration in gas phase of 6% by volume and was finished when the total amount of fed propylene reached 28 kg.

The resulting polymerization slurry was immediately introduced into an after-treatment vessel, polymerization was terminated with butanol. After having been treated at 60°C for 3 hours, the resulting slurry was washed with water. Separating the solid from liquid gave 8.5 kg of a polymer mixture.

The content of vinylcyclohexane polymer in the polymer mixture was 10,500 ppm.

To 100 parts by weight of the polymer mixture obtained above were added 0.1 part by weight of calcium stearate, 0.2 part by weight of Sumilizer® BHT and 0.05 part by weight of Irganox® 1010, and mixed with a Henschel mixer to obtain a composition. The composition was melt-extruded to obtain pellets.

The pellets showed a melt flow rate of 6.5 g/10 min., a melting point of 167°C, a crystallization temperature of 135°C, and a CXS of 2.1% by weight.

The pellets were melt-extruded through a sheet extruder having a screw part diameter of 40 mm at a die temperature of 280°C. Then, the extruded sheet was cooled with a cooling roll at 30°C to obtain a sheet 0.5 mm in thickness.

The sheet obtained above was stretched 5-fold in the longitudinal direction (MD) and 5-fold in the transversal direction (TD) with a bench-type biaxial stretching apparatus at a stretching temperature of 150°C to obtain a biaxially

stretched film of about 20 μm thickness. Table 1 shows the results of the determination of the transparency and rigidity of the film obtained.

Comparative Example 1

A film was prepared and evaluated in the same manner as in Example 1 except that a crystalline propylene polymer of a melt flow rate of 2.3 g/10 min (Sumitomo Noblen FS2011A) was used alone in place of the composition used in Example 1.

The results of evaluation are shown in Table 1.

Example 2

A polymer mixture having a vinylcyclohexane polymer concentration of 23,400 ppm by weight and ethylene content of 0.7% by weight was prepared in the same manner as in Example 1 using the solid catalyst (b) of Example 1 except that the hydrogen concentration was altered and a gas mixture of propylene with a small amount of ethylene was fed.

The film was prepared in the same manner as in Example 1 except that a composition comprising the polymer mixture prepared above was used. The film thus obtained was evaluated in the same manner as in Example 1. Table 1 shows the results of the evaluation.

Comparative Example 2

Propylene was polymerized in the same manner as in the preparation of the polymer mixture in Example 1 except that the solid catalyst (a) of Example 1 was used, the polymerization temperature was altered to 55°C and the hydrogen concentration was changed. The polymer obtained had an isotactic pentad fraction of boiling heptane insoluble portion of 0.973 and a content of boiling heptane soluble portion of 4.9% by weight as determined by the method described in JP-A-55-81125.

A film was prepared by using the polymer obtained above in the same manner as in Example 1 and the film was evaluated in the same manner as in Example 1. The results of evaluation are shown in Table 1.

Comparative Example 3

A film was prepared in the same manner as in Example 1 except for using a composition which consists of 100 parts by weight of the crystalline propylene polymer of Comparative Example 1 and 0.25 part by weight of the polymer mixture of Example 1. The film thus obtained was evaluated in the same manner as in Example 1. The results of evaluation are shown in Table 1.

Comparative Example 4

A crystalline propylene polymer having a melt flow rate of 1.0 g/10 min was obtained by polymerizing propylene in the same manner as in Example 2 except for using the solid catalyst (a) of Example 1 (Comparative Example 4). Films were prepared in the same manner as in Example 1 by using the above propylene polymer alone or the polymer mixture obtained above. The films were evaluated in the same manner as in Example 1. Table 1 shows the results of the evaluation.

Comparative Example 5

A polymer mixture was obtained by adding to the polymer mixture of Example 1 2.5% by weight of the cold xylene solubles extracted from the crystalline propylene polymer of Comparative Example 1. To 100 parts by weight of the polymer mixture were added 0.1 part by weight of calcium stearate, 0.2 part by weight of Sumilizer® BHT and 0.05 part by weight of Irganox® 1010. Then, the resulting mixture was melt-blended with a roll blender at 200°C to obtain a composition. The composition was melt-formed with a hot press at 230°C and cooled at 30°C to obtain a pressed sheet of 0.5 mm thickness. The sheet was stretched in the same manner as in Example 1 and the resulting film was evaluated. The results of evaluation are shown in Table 1.

Comparative Example 6

A film was prepared in the same manner as in Example 1 except for using a polymer mixture of the crystalline propylene polymer of Comparative Example 1 and 10% by weight of Arcon® P-115 (an alicyclic petroleum resin) in

place of the polymer mixture used in Example 1. The film thus obtained was evaluated in the same manner as in Example 1. Table 1 shows the results of the evaluation.

Thus, a polypropylene stretched film according to the present invention having a high rigidity and a beautiful appearance including transparency can be obtained without impairing the characteristic properties inherent to crystalline propylene polymers by stretching a composition comprising a specified crystalline propylene polymer and a specified nucleating agent in a specified ratio.

Table 1

Example No.	Composition (including compositions containing a crystalline propylene polymer alone)						Properties of film	
	MFR g/10 min	Nucleating agent		T _m (°C)	T _c (°C)	CXS (wt%)	LSI (%)	Young's modulus (MD) 2 (kg/cm ²)
Example 1	6.5	Vinylcyclohexane polymer	Type	167	135	2.1	1.1	28,500
Example 2	2.5			164	132	2.5	1.2	26,000
Compara- tive Example 1	2.3	-	-	161	117	3.2	11.3	22,500
Compara- tive Example 2	1.5	-	-	165	120	1.0	8.5	24,900
Compara- tive Example 3	2.3	Vinylcyclohexane polymer	Type	163	127	3.2	3.5	22,800
Compara- tive Example 4	1.0			167	125	1.6	15.1	24,700
Compara- tive Example 5	9.1	Vinylcyclohexane polymer	Type	166	135	4.6	2.2	24,100
Compara- tive Example 6	4.0			159	112	-	6.8	25,000

Claims

1. A polypropylene stretched film consisting essentially of a composition which comprises a crystalline propylene polymer and a polymer of a vinylcycloalkane, the composition having a melting point of 160°C or more, a crystallization temperature of 128°C or more and a 20°C xylene soluble portion of 3.0% by weight or less, characterised in that the film is transparent and the vinylcycloalkane polymer is a vinylcycloalkane polymer which is present in an amount from 10,500 ppm to 10% by weight.
2. A film according to Claim 1, wherein the amount of vinylcycloalkane polymer present is from 10,500 ppm to 23,400 ppm.
3. A film according to Claim 1 or Claim 2, wherein the melt flow rate of the composition is 10 g/10 min or less.
4. A film according to Claim 1, wherein the melting point of the composition is 164°C or more.
5. A film according to Claim 4, wherein the melting point of the composition is 166°C or more.
6. A film according to Claim 1, wherein the 20°C xylene soluble portion of the composition is 2.5% by weight or less.

Patentansprüche

1. Gereckte Polypropylenfolie, die im wesentlichen aus einer Zusammensetzung besteht, die ein kristallines Propylenpolymer und ein Polymer eines Vinylcycloalkans umfaßt, wobei die Zusammensetzung einen Schmelzpunkt von 160°C oder mehr, eine Kristallisationstemperatur von 128°C oder mehr und einen in Xylol mit 20°C löslichen Teil von 3.0 Gew.-% oder weniger aufweist, dadurch gekennzeichnet, daß die Folie transparent ist und das Vinylcycloalkanpolymer ein Vinylcycloalkanpolymer ist, das in einer Menge von 10500 ppm bis 10 Gew.-% vorhanden ist.
2. Folie nach Anspruch 1, in der die Menge des vorhandenen Vinylcycloalkanpolymers 10500 ppm bis 23400 ppm beträgt.
3. Folie nach Anspruch 1 oder 2, in der der Schmelzindex der Zusammensetzung 10 g/10 min oder weniger beträgt.
4. Folie nach Anspruch 1, in der der Schmelzpunkt der Zusammensetzung 164°C oder mehr beträgt.
5. Folie nach Anspruch 4, in der der Schmelzpunkt der Zusammensetzung 166°C oder mehr beträgt.
6. Folie nach Anspruch 1, in der der in Xylol mit 20°C lösliche Anteil der Zusammensetzung 2.5 Gew.-% oder weniger beträgt.

Revendications

1. Film de polypropylène étiré constitué essentiellement d'une composition comprenant un polymère de propylène cristallin et un polymère de vinylcycloalcane, la composition ayant un point de fusion de 160°C ou plus, une température de cristallisation de 128°C ou plus et une partie soluble dans le xylène à 20°C de 3,0% en poids ou moins, caractérisé en ce que le film est transparent et le polymère de vinylcycloalcane est un polymère de vinylcycloalcane présent en une quantité de 10 500 ppm à 10% en poids.
2. Film selon la revendication 1, dans lequel la quantité de polymère de vinylcycloalcane présent vaut de 10 500 ppm à 23 400 ppm.
3. Film selon la revendication 1 ou 2, dans lequel le taux de fluidité à chaud de la composition est de 10 g / 10 min ou moins.
4. Film selon la revendication 1, dans lequel le point de fusion de la composition vaut 164°C ou moins.

EP 0 369 658 B1

5. Film selon la revendication 4, dans lequel le point de fusion de la composition vaut 166°C ou moins.
6. Film selon la revendication 1, dans lequel la partie soluble de la composition dans le xylène à 20°C vaut 2,5% en poids ou moins.

5

10

15

20

25

30

35

40

45

50

55